

**TÜV SÜD America Inc.****Product Safety Services**

1755 Atlantic Blvd.

Auburn Hills, MI 48326

Phone: (616) 546-4600

**SURFACING MATERIAL REPORT – ASTM F1292-18**

Client: Everplay  
Manufacturer: Everplay  
Manufacturing Location: Brampton, ON, CAN  
Phone: (416) 410-3056  
Commercial Name of product: EVERPLAY "in situ" - 14ft.  
Date of Manufacture: Unknown  
No. of samples submitted: 3 - 22.5in. X 22.5in. Samples

Project No.: 72154519-1  
Report Date: 11/12/2019  
Test Date: 11/12/2019  
Initial Test: ☒  
Follow up Test: ☐ **Ref Job:**  
Sample Receipt Date: 11/4/2019  
Ambient Air Temperature: 20.9°C  
Humidity: 20.0%

**Test Equipment:**

Triax System 5:	<input checked="" type="checkbox"/>	Environmental Chamber ID:	<b>PLYP00069</b>
Triax System 4:	<input type="checkbox"/>	Calibration Due Date:	<b>9/9/2020</b>
Accelerometer ID:	<b>PLYP00117</b>	Environmental Chamber ID:	<b>PLYP00101</b>
Accelerometer Calibration Date:	<b>5/16/2019</b>	Calibration Due Date:	<b>9/9/2020</b>

**Loose Fill Material Sample Description:**

Engineered Wood Fiber:	<input type="checkbox"/>	Un-compacted Depth:	Inches
Loose Fill Wood:	<input type="checkbox"/>		
Rubber:	<input type="checkbox"/>		
Sand:	<input type="checkbox"/>	Compacted Depth:	Inches
Gravel:	<input type="checkbox"/>		
Other:	<input type="checkbox"/>		

**Unitary Sample Description:**

Tiles	<input type="checkbox"/>	Total Thickness:	<u>7.0in.</u>
Poured in Place	<input checked="" type="checkbox"/>	Top Layer:	<u>See Comments</u>
Other	<input type="checkbox"/>	Base Layer:	<u>See Comments</u>

**Comments:**

- 1.) System: 38mm (1.5in.) wear layer, comprised of two material types approximately 19mm (0.75in) thick, overlaying 140mm (5.5in.) recycled rubber. Total system depth/thickness of 7.0in.
- 2.) Samples were provided by Customer in assembled wooden box, and tested as received.
- 3.) System description: Cushion layer of recycled rubber bound with polyurethane with low compaction wear layer of rubber granule bound with UV stable polyurethane densely packed.

**The above described sample was tested at :    14    Ft.**

The results reported herein reflect the performance of the above described samples at the time of testing and at the temperature(s) reported. The results are specific to the described samples. Samples of surfacing materials that do not closely match the described samples will perform differently. The following data sheet provides an accurate representation of the test results. Compliance with this Standard does not constitute product certification.

Sample in compliance with ASTM F1292-18 at the temperature and rating specified?      Yes      ☒      No      ☐

Signature: Timothy FranklinTitle: Project CoordinatorDate: 11/12/2019Reviewed by: [Signature]Title: Regional ManagerDate: 11/12/2019

Client: **Everplay**Project No.: **72154519-1**Manufacturer: **Everplay**Test Date: **11/12/2019**

Drop	Specified Impact Height (ft.)	Reference Temperature -6°C, (21.2°F)				Reference Temperature 23°C, (73.4°F)				Reference Temperature 49°C, (120.2°F)			
		G-Max	HIC	Velocity (ft/s)	Theoretical Drop Height (ft.)	G-Max	HIC	Velocity (ft/s)	Theoretical Drop Height (ft.)	G-Max	HIC	Velocity (ft/s)	Theoretical Drop Height (ft.)
1	14	77	570	29.9	13.898	68	503	29.9	13.898	65	423	30.0	13.991
2	14	78	574	30.0	13.991	66	461	30.0	13.991	64	422	30.0	13.991
3	14	77	563	30.0	13.991	65	452	29.9	13.898	63	412	30.0	13.991
Average		77.5	568.5			65.5	456.5			63.5	417		
Measured Surface Temperature		(-5°C)	Max. Change from reference + 5°C, (5°F)				23°C	Max. Change from reference ± 3°C, (5°F)				48°C	Max. Change from reference -3°C, (-5°F)
Sample Condition:		DRY				DRY				DRY			

Drop	One foot over (ft.)	Reference Temperature -6°C, (21.2°F)				Reference Temperature 23°C, (73.4°F)				Reference Temperature 49°C, (120.2°F)			
		G-Max	HIC	Velocity (ft/s)	Theoretical Drop Height (ft.)	G-Max	HIC	Velocity (ft/s)	Theoretical Drop Height (ft.)	G-Max	HIC	Velocity (ft/s)	Theoretical Drop Height (ft.)
1					0.000				0.000				0.000
2					0.000				0.000				0.000
3					0.000				0.000				0.000
Average		0	0			0	0			0	0		
Measured Surface Temperature		°C	Max. Change from reference + 5°C, (5°F)				°C	Max. Change from reference ± 3°C, (5°F)				°C	Max. Change from reference -3°C, (-5°F)
Sample Condition:													

Drop	One foot under (ft.)	Reference Temperature -6°C, (21.2°F)				Reference Temperature 23°C, (73.4°F)				Reference Temperature 49°C, (120.2°F)			
		G-Max	HIC	Velocity (ft/s)	Theoretical Drop Height (ft.)	G-Max	HIC	Velocity (ft/s)	Theoretical Drop Height (ft.)	G-Max	HIC	Velocity (ft/s)	Theoretical Drop Height (ft.)
1					0.000				0.000				0.000
2					0.000				0.000				0.000
3					0.000				0.000				0.000
Average		0	0			0	0			0	0		
Measured Surface Temperature		°C	Max. Change from reference + 5°C, (5°F)				°C	Max. Change from reference ± 3°C, (5°F)				°C	Max. Change from reference -3°C, (-5°F)
Sample Condition:													

